


# PRIMARY MFG

## CE 221 DLS

High dielectric strength  
Stiff  
Heat resistance



**Tensile strength** 92 ± 13 MPa

**Elongation At break** 3.3 ± 0.8%

**Flexural strength** 131 ± 27 MPa

**HDT** 231°C

**Hardness** 92, Shore D

Comparable to 14% glass-filled nylon 6, CE 221 is a stiff material that maintains its properties to 231°C. CE 221 is perfect for electronic enclosures, industrial products, and under-the-hood components.

