


PRIMARY MFG

RPU 70 DLS

More heat resistant...

Better looking...

And stiffer than RPU 60



Tensile strength 45 ± 2 MPa

Elongation At break 100 ± 20%

Flexural strength 62 ± 9 MPa

Impact Strength 22 ± 1 J/m
Notched Izod (machined)

Hardness 80, Shore D

RPU 70 is the stiffer alternative to RPU 60, and also features a higher heat deflection temperature of 70°C. Common applications are automotive and industrial.

