

PRIMARY MFG



Material tech data sheet

TOUGH-BLK 20 DLS

ABS-like
Long-term UV stability
Quick Building



Tensile strength 40 MPa

Elongation At break 36%

Flexural strength 61 MPa

Impact strength 27 J/m
Notched Izod

Hardness 79, Shore D

To get the quality and strength of an ABS injection molded part without the tooling cost, TOUGH-BLK 20 is a no-brainer. Parts come out with exceptional surface quality, and are perfect for prototyping or even production.

